



# DELHI TEST HOUSE<sup>®</sup>



A-62/3, G.T. Karnal Road, Industrial Area, Opp. Hans Cinema, Azadpur, Delhi-110 033 (INDIA)  
Phone : +91-11-47075555 (30 Lines) Fax : +91-11-47075550  
e-mail : info@delhitesthouse.com

QR-0302

Issued to:  
The Manager  
Jindal Mechno Bricks Pvt. Ltd.  
Village Badli Distt.  
Jhajjar, Hariyana

Report No : 20467111217GEN821  
Date : 27-12-2011  
Date of Receipt : 17-12-2011  
Party Ref No : NIL

Sample Description:-TILES T/C (9"X 4.5"), (40 mm THICK)

## TEST REPORT

Sl.no	Tests	Test Values	Test Method
<b>1.PARAMETER</b>			
1	Compressive Strength, Kg/cm <sup>2</sup>	: 625.0	IS:3495(P-1)-92
2	Compressive Strength, Kg/cm <sup>2</sup>	: 632.6	IS:3495(P-1)-92
3	Compressive Strength, Kg/cm <sup>2</sup>	: 610.0	IS:3495(P-1)-92
4	Compressive Strength, Kg/cm <sup>2</sup>	: 615.7	IS:3495(P-1)-92
5	Compressive Strength, Kg/cm <sup>2</sup>	: 626.9	IS:3495(P-1)-92
6	Water absorption,(%)	: 7.4	IS:3495(P-2)-92
7	Water absorption,(%)	: 8.8	IS:3495(P-2)-92
8	Water absorption,(%)	: 9.1	IS:3495(P-2)-92
9	Water absorption,(%)	: 8.9	IS:3495(P-2)-92
10	Water absorption,(%)	: 10.3	IS:3495(P-2)-92

Any deviation from the Standard Test Method / Specification - Nil  
RAJ/VAS-210467-JYO-682012011088 dos/doc 18-DEC-11--27-DEC

G. D. GOEL  
  
Authorised Signatory  
Director-tech